



耐化学性图表

Chemical resistance chart

LEGENDA									
A	优异 / Excellent								
B	优良 / Good								
C	适用 / Suitable								
X	请勿使用 / Do not use								

Media	Ester-PUR	Ether-PUR	Soft-PVC	TPV	Hypalon	Silicon	TPE				
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C
acetaldehyde, aqueous	B	X	B	X	B	X	A	B	B	X	-
acetamide	X	-	X	-	X	-	A	-	B	-	-
acetic acid 10%	X	-	B	C	A	C	A	-	B	B	C
acetic acid 100%	X	-	X	-	X	-	X	-	B	C	X
acetic acid 3%	C	X	A	B	A	B	A	-	A	A	X
acetic acid ethyl ester (ethyl acetates)	X	-	X	-	X	-	B	X	X	-	C
acetic anhydride	X	-	X	-	X	-	A	B	A	A	A
acetone	X	-	X	-	X	-	B	C	-	-	X
acetylacetone	X	-	X	-	X	-	-	-	-	X	-
acetylene	A	A	A	B	C	A	-	A	B	A	-
acids, generally (see exact media)	C	-	B	C	A	B	B	C	A	B	X
acrylic acid ethylester	X	-	X	-	X	-	C	X	C	X	-
acrylic esters (ethyl acrylate)	X	-	X	-	X	-	A	-	A	-	B
acrylonitrile	X	-	X	-	X	-	C	X	B	C	-
adipic acid, aqueous	C	-	B	C	A	B	A	A	A	A	X
Aethylenediamine	A	-	A	-	A	-	A	-	B	-	C
air, containing oil - oil	A	-	X	-	X	-	X	-	B	-	C
air, dry	A	A	A	A	A	A	A	A	A	A	-
alcohols, generally (see exact media)	B	X	B	X	B	X	A	B	A	B	X
aliphatics, generally (see exact media)	A	B	A	B	C	X	C	X	B	X	-
alkalis, generally (see exact media)	B	C	A	B	A	B	B	B	A	B	X
allyl alcohol	C	X	C	X	C	X	A	A	A	C	X
allyl chloride	X	-	X	-	X	-	B	X	A	X	A
alum, aqueous	A	B	A	A	A	B	A	A	A	A	-
aluminum acetates	C	-	B	-	A	A	A	-	A	-	-
aluminum chloride, 10%	B	C	A	B	A	A	A	-	A	-	X
aluminum fluoride	C	X	C	X	A	-	A	-	A	-	C
aluminum hydroxide	C	X	B	X	A	-	-	-	A	-	A
aluminum nitrate	C	-	B	-	A	-	-	-	A	-	B
aluminum phosphates	B	-	A	-	A	-	A	-	A	-	-
aluminum sulfate, aqueous	B	X	A	C	A	A	A	B	A	A	-
aminoethanols	X	-	X	-	X	-	A	-	C	-	X
ammonia, aqueous 100%	X	-	X	-	A	A	A	A	C	-	-
ammonia, aqueous 3% (liquid ammonia)	C	-	A	B	A	A	A	C	X	A	-
ammonia, gaseous	B	X	A	C	A	A	A	B	A	A	B
ammonium acetate, aqueous	X	-	C	X	A	A	A	A	-	C	X
ammonium carbonate, aqueous	X	-	C	X	A	B	A	A	A	B	X
ammonium chloride, aqueous 3% (salmicac)	A	B	A	B	A	A	A	A	A	A	-
ammonium diphosphat, aqueous	C	-	A	-	A	-	-	-	A	-	-
ammonium fluorides, aqueous	X	-	X	-	A	C	A	A	A	A	-
ammonium metaphosphat, aqueous	A	-	A	-	-	-	-	-	A	-	-
ammonium nitrate, aqueous	C	X	B	X	A	A	A	A	A	A	-
ammonium phosphates, aqueous	B	X	B	X	A	A	A	A	A	A	-
ammonium sulfate	A	X	A	C	A	A	A	A	-	A	-
ammonium thiocyanate	C	-	B	-	A	-	-	-	A	-	-
amyl alcohols - pentanols	-	-	-	-	-	-	-	-	-	-	X
amyl chlorides	X	-	X	-	X	-	-	-	X	-	X
aniline	X	-	X	-	X	-	-	-	B	C	-
aniline hydrochloride	X	-	X	-	B	X	-	-	X	-	-
anole - cyclohexanol (see cyclohexanol)	-	-	-	-	-	-	-	-	-	-	-
anone - cyclohexanone (see cyclohexanone)	-	-	-	-	-	-	-	-	-	-	-
anthraquinonesulfonics acid, aqueous	X	-	X	-	A	-	A	-	X	-	-
antifreezes - see exact media	-	-	-	-	-	-	-	-	-	-	-
antimony chlorides, free of water	X	-	X	-	A	A	A	A	B	C	X

Media	Ester-PUR	Ether-PUR	Soft-PVC	TPV	Hypalon	Silicon	TPE				
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C
antimony-III-chlorides, aqueous	C	X	B	X	A	A	A	A	A	B	X
aqua fortis (see nitric acid)	-	-	-	-	-	-	-	-	-	-	-
aqua regia (nitrohydrochloric acid)	X	-	X	-	X	-	X	-	C	-	C
argon	A	-	A	-	A	-	A	-	A	-	A
aromatics, generally (see exact media)	X	-	X	-	X	-	C	X	C	X	-
arsenic acid, aqueous	C	X	C	X	A	B	A	A	A	B	X
asphalt	B	X	B	X	B	C	B	X	C	X	-
ASTM-oils (see oil)	-	-	-	-	-	-	-	-	-	-	-
ATE-brake fluids - brake fluids	X	-	X	-	A	-	-	-	A	-	C
barium chloride, aqueous	A	C	A	C	A	A	A	A	A	A	-
barium hydroxide, aqueous	C	X	B	C	A	A	A	A	A	A	-
barium sulfate	A	-	A	-	A	-	B	-	A	-	A
barium sulfide	C	X	B	C	A	-	A	-	A	-	A
basic aluminium acetate (see aluminium acetates)	-	-	-	-	-	-	-	-	-	-	-
battery acid - sulfuric acid	X	-	X	-	C	X	B	C	B	C	X
beef tallow (beef fat) - (see oil, animal)	-	-	-	-	-	-	-	-	-	-	-
beer	A	-	A	-	A	A	A	-	A	-	A
benzaldehyde	X	-	X	-	X	-	A	-	X	-	X
benzene	X	-	X	-	X	-	X	-	X	-	X
benzoic acid, aqueous	C	X	B	C	A	B	A	A	A	C	X
benzyl alcohol	X	-	X	-	C	X	A	C	A	-	A
benzyl benzoate	X	-	X	-	-	-	-	-	A	-	A
benzylchloride	X	-	X	-	A	-	X	-	X	-	B
bismuth carbonates	A	-	A	-	A	-	-	-	-	A	-
bitumen (asphalt)	B	X	B	X	B	C	B	X	C	X	C
black liquor (cellulose-/ pulp-production)	X	-	X	-	-	-	-	-	X	A	X
bone oils	A	-	A	-	B	-	X	-	-	B	C
borax, aqueous	B	C	A	A	A	-	A	-	-	A	-
boric acid, aqueous	B	C	A	B	A	A	A	A	A	A	-
brake fluid, ATF-	X	X	X	X	A	-	A	A	A	A	B
brake fluid, ATS-	X	X	X	X	A	-	A	-	B	-	-
brake fluid, out of glycol ethers	X	-	X	-	-	-	-	-	-	-	-
bromine	X	-	X	-	X	-	X	-	C	X	X
bromine water	X	-	X	-	X	-	-	-	B	-	X
bromobenzene	X	-	X	-	X	-	C	X	-	-	X
bromochloromethane	X	-	X	-	X	-	C	X	X	-	X
butadiene	B	C	A	B	A	A	C	X	A	A	C
butane, gaseous	A	-	A	-	C	X	C	X	A	-	X
butane, liquid	A	-	A	-	B	-	-	-	A	-	C
butene, aqueous	A	-	A	-	B	-	X	-	A	-	C
butter	B	-	A	-	B	-	A	-	B	-	A
butter milk	B	-	A	-	B	-	A	-	B	-	A
butyl acetates	X	-	X	-	X	-	-	-	X	-	X
butyl benzoate	A	-	A	-	-	-	-	-	X	-	X
butyl carbitol	X	-	X	-	-	-	-	-	B	-	B
butyl oleate	X	-	X	-	-	-	-	-	X	-	A
butyl phenol	X	-	X	-	C	X	-	-	X	-	X
butyl stearate	A	-	A	-	A	-	-	-	B	-	X
butylalcohol	B	C	B	C	B	C	-	-	A	A	B
butylamine	B	-	B	-	X	-	-	-	-	B	-
butylether	X	-	C	-	A	-	-	-	-	C	-
butylglycol, aqueous	A	-	A	-	C	-	A	B	A	A	B
butylglycol, aqueous	X	-	X	-	B	-	X	-	X	-	B
butynediol	A	-	A	-	-	-	-	-	B	-	-

Media	Ester-PUR		Ether-PUR		Soft-PVC		TPV		Hypalon		Silicon		TPE	
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C	80 °C
butyraldehyde	X	-	X	-	-	-	C	-	C	X	-			
butyric acid	C	X	B	C	A	C	-	-	C	-	C	-	B	
calcium acetate	B	-	B	-	A	A	-	-	B	-	C	X	-	
calcium bisulfate, aqueous	C	X	B	C	A	-	A	-	A	-	A	-	X	
calcium bisulphite, aqueous	C	-	C	-	A	-	-	-	A	-	B	-	X	
calcium carbonate	A	-	A	-	A	A	X	-	A	-	A	-		
calcium chloride, aqueous 10%	B	X	A	C	A	A	A	A	A	-	A	-		
calcium hydroxide, aqueous	A	C	A	B	A	A	A	-	A	-	B	-		
calcium hypochlorite	X	-	X	-	A	A	-	-	A	-	C	X	-	
calcium nitrate	A	-	A	-	A	A	A	-	A	-	A	A	-	
calcium oxide (lime)	A	-	A	-	A	-	-	-	A	-	B	-	B	
calcium phosphates, aqueous	B	-	B	-	-	-	A	-	A	-	A	-		
calcium sulfate	A	-	A	-	A	-	-	-	A	-	A	-		
calcium sulfide	A	-	A	-	A	-	-	-	A	-	A	-		
camphor	X	-	X	-	-	-	C	X	-	-				
caritol	X	-	X	-	C	-	-	-	B	-	B	-		
carbon dioxide, dry	A	A	A	A	A	A	A	A	A	A	A	A	B	
carbon dioxide, wet (carbonic acid)	B	-	A	-	A	A	A	A	A	A	-			
carbon disulfite	X	-	X	-	X	-	X	-	X	-	X	-		
carbon oxide (carbon monoxide)	A	A	A	A	A	A	A	A	A	A	A	-		
caro's acid	-	-	-	-	A	-	-	-	B	-	-	-		
castor oil	A	-	A	-	B	C	B	-	A	-	A	-		
caustic potash (see potash lye)	-	-	-	-	-	-	-	-	-	-	-	-		
celluloseacetate	A	-	A	-	-	-	-	-	-	-	A	-		
chloral hydrate	X	-	X	-	X	-	-	-	B	-	-	-		
chloramine, aqueous	B	-	B	-	-	-	A	-	A	-	-	-		
chloric acid, aqueous	X	-	C	X	A	B	X	-	A	C	X	-		
chloride of lime (bleach)	X	-	X	-	B	C	A	-	A	A	X	X	-	
chlorinated water	X	-	C	-	B	C	C	X	B	-	C	-		
chlorine oxides	X	-	X	-	B	-	-	-	A	-	C	-		
chlorine, aqueous	X	-	X	-	X	-	X	-	C	X	X	-	B	
chlorine, gaseous dry	X	-	X	-	X	-	X	-	C	-	X	-	B	
chloroacetic acid, mono	X	-	X	-	A	C	A	-	B	-	X	-	B	
chlorobenzene	X	-	X	-	X	-	X	-	X	-	X	-	X	
chloroform (trichloromethanes) (see chloromethanes)	-	-	-	-	-	-	-	-	-	-	-	-	X	
chloromethanes (chloroform, dichloromethane)	X	-	X	-	X	-	X	-	X	-	X	-		
chloroprene (chlorobutadiene)	X	-	X	-	X	-	X	-	B	-	X	-		
chlorosulfuric acid	X	-	X	-	X	-	X	-	X	-	X	-	B	
chromic acid 10%	X	-	C	X	A	-	B	C	A	-	B	-	B	
chromic acid 17%	X	-	X	-	A	-	C	X	X	-	A	-	B	
chromic acid 50%	X	-	X	-	X	-	X	-	X	-	B	-		
citric acid, aqueous	B	X	A	C	A	A	A	-	B	-	B	-		
coal tar	C	-	C	-	B	-	-	-	C	-	A	-		
coconut oil	A	A	A	A	A	-	B	C	C	-	A	A	-	
coconuts fatty alcohol	X	-	X	-	A	B	A	-	-	-	A	A	-	
copper acetates, aqueous	B	-	B	-	A	-	A	-	-	C	-			
copper chloride, aqueous	A	-	A	-	A	-	A	A	A	-	A	-		
copper cyanide	C	-	A	-	A	-	-	-	A	-	A	-		
copper fluoride, aqueous	X	-	X	-	-	-	A	A	A	-	A	-		
copper hydroxide	A	-	A	-	-	-	-	-	-	-	-	-		
copper nitrate, aqueous	C	X	C	X	C	-	A	A	A	-	A	-		
copper sulfate, aqueous	B	-	B	-	B	C	A	A	A	-	A	A	-	
cottonseed oil	A	-	A	-	A	A	-	-	C	-	A	-		
creosote (coal tar)	X	-	X	-	X	-	-	-	C	-	A	-		
cresols	X	-	X	-	X	-	C	X	C	-	A	-	X	
crotonaldehyde (butenal)	C	X	B	C	X	-	-	-	A	-	A	-		
cyclohexane	A	B	A	B	X	-	B	X	X	-	A	-	X	
cyclohexanol	C	X	B	X	X	-	A	A	B	-	X	-	X	
cyclohexanone	X	-	X	-	X	-	B	X	X	-	X	-	X	
cyclohexylamine	X	-	X	-	A	-	-	-	-	-	X	-		
DEKALIN	X	-	X	-	A	-	-	-	X	-	A	-		
detergents, generally (see exact media)	B	C	A	B	A	C	A	A	A	-	A	-		

Media	Ester-PUR		Ether-PUR		Soft-PVC		TPV		Hypalon		Silicon		TPE	
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C	80 °C
developing dyes, generally (see exact media)	B	-	B	-	A	-	A	-	A	-	A	-	A	-
dextrin, aqueous	-	-	-	-	A	-	A	A	-	-	A	-	A	-
diacetone alcohol	B	X	B	X	X	-	-	-	C	-	X	-	B	-
dibenzylether	X	-	X	-	X	-	-	-	X	-	A	-		
dibutyl ether	X	-	X	-	B	X	C	X	-	-	X	-		
dibutylamine	X	-	X	-	-	-	-	-	X	-	X	-		
dichloroacetic acid	X	-	X	-	-	-	B	C	X	-	C	X	-	
dichlorobenzenes	X	-	X	-	X	-	C	X	-	-	B	-		
dichloroethanes	X	-	X	-	X	-	C	X	-	-	B	-		
dichloroethylenes	X	-	X	-	X	-	X	-	X	-	B	-		
diethyl ether	A	-	A	-	X	-	C	-	C	-	X	-		
diethylamine	X	-	X	-	X	-	-	-	X	-	X	-		
diethylbenzene	X	-	X	-	A	-	-	-	X	-	X	-		
diethylene glycol	C	-	C	-	B	-	A	A	A	-	A	-		
diglycolic acid, aqueous	A	-	A	-	A	C	A	A	-	-	A	-		
dimethyl ether	C	-	C	-	X	-	-	-	X	-	X	-		
dimethylamine	X	-	X	-	X	-	C	X	X	-	X	-		
dimethylanilin (xylidines)	B	-	B	-	X	-	-	-	X	-	B	-		
dimethylformamide	X	-	X	-	X	-	C	X	-	-	X	-		
dimethylheptanon	X	-	X	-	X	-	C	X	-	-	X	-		
dioxane	X	-	X	-	X	-	B	C	X	-	X	-		
diphenyl	X	-	X	-	X	-	-	-	X	-	A	-		
diphenyl chloride	X	-	X	-	X	-	-	-	X	-	A	-		
diphenyl ether	X	-	X	-	X	-	B	C	X	-	B	-		
dipropylene glycol	-	-	-	-	-	-	-	-	-	-	A	-		
dodecanol (laurylalcohol, 1-dodecanol)	A	-	A	-	A	-	A	A	A	-	A	-		
epichlorhydrin	X	-	X	-	X	-	-	A	-	X	X	-		
essential oil of, generally	B	-	B	-	X	-	C	-	X	-	A	-	B	-
ethane	A	-	A	-	A	-	A	-	B	-	A	-		
ethanol 100%	B	X	A	C	C	X	B	X	A	B	-	A	-	A
ethanol 50%	B	X	A	C	B	X	A	B	-	-	A	-	A	-
ethanol, 10% (ethyl alcohol, spirit)	B	C	A	B	A	A	-	-	A	A	A	-	A	-
ethyl chloride	X	-	X	-	X	-	C	X	C	-	A	-	B	-
ethylbenzene	X	-	X	-	X	-	X	-	X	-	X	-		
ethylbromide	B	-	B	-	X	-	-	-	X	-	B	-	X	-
ethylene	A	-	A	-	A	-	-	-	X	-	B	-		
ethylene chloride dichloroethanes	-	-	-	-	-	-	-	-	X	-	B	-	B	-
ethylene chlorohydrin	X	-	X	-	X	-	B	-	B	-	X	-	B	-
ethylene glycol (glycol)	B	X	A	C	B	-	A	A	A	A	A	A	B	-
ethylene oxide, gaseous	A	-	A	-	A	-	A	-	A	-	A	-	B	-
fatty acids with 1-7 C-atoms, generally	C	X	B	C	A	-	-	-	C	-	C	-	B	-
fatty acids with >7 C-atoms, generally	B	C	A	B	A	-	-	-	C	-	C	-	B	-
fatty alcohols, generally (see exact media)	C	-	B	-	B	-	C	-	B	-	B	-		
fermentation gas (marsh gas)	A	-	A	-	A	-	A	A	A	A	A	A	-	
fertilizing salt, aqueous	X	-	C	X	A	A	A	A	A	A	A	A	-	
fish liver oil	A	-	A	-	X	-	A	-	B	-	B	-		
fish needle oil	B	-	B	-	X	-	-	-	X	-	C	-		
fluorbenzene	X	-	X	-	-	-	X	-	X	-	X	-		
Fluoride of boron acid 65%	X	-	X	-	A	-	-	-	B	-	X	-		
fluorine, gaseous	X	-	X	-	C	-	X	-	X	-	C	-		
fluorosilicic acid, aqueous	X	-	X	-	A	A	-	-	A	B	B	C	A	
formaldehyde, aqueous	B	X	B	X	B	C	A	A	A	-	A	B	A	
formamide	X	-	X	-	X	-	A	A	A	A	-	-		
formic acid, 10%														

Media	Ester-PUR	Ether-PUR	Soft-PVC	TPV	Hypalon	Silicon	TPE				
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C
furan	X	-	X	-	A	-	-	X	-	-	-
furfrol	X	-	X	-	X	-	C	-	C	-	-
gallic acid	X	-	C	X	A	-	-	A	-	B	-
gasoline, ASTM-Fuel A	A	-	A	-	X	X	X	-	A	-	C
gasoline, ASTM-Fuel B	C	-	X	-	X	X	X	-	X	-	C
gasoline, ASTM-Fuel C	X	-	X	-	X	X	X	-	X	-	X
gasoline, diesel/ diesel oil/ heating oil	C	-	X	-	X	X	X	-	X	-	C
gasoline, FAM-Fuel DIN 51604-A	A	-	A	-	X	X	X	-	-	-	-
gasoline, FAM-Fuel DIN 51604-B	B	-	B	-	X	X	X	-	-	-	-
gasoline, FAM-Fuel DIN 51604-C	X	-	X	-	X	X	X	-	-	-	-
gasoline, flight- (kerosene)	X	-	X	-	X	X	X	-	X	-	C
gasoline, generally (see exact media)	X	-	X	-	X	X	X	-	X	-	C
gasoline, white spirits	X	X	X	X	X	X	X	-	X	-	-
gasoline-benzene (50/ 50%)	X	-	X	-	X	X	X	-	X	-	X
gasoline-benzene (60/ 40%)	X	-	X	-	X	X	X	-	X	-	X
gasoline-benzene (70/ 30%)	X	-	X	-	X	X	X	-	X	-	C
gasoline-benzene (80/ 20%)	X	-	X	-	X	X	X	-	X	-	C
gasoline-benzene-ethanol (50/30/20%)	X	-	X	-	X	X	X	-	X	-	X
gelatin	B	C	A	B	X	-	A	A	A	-	A
glucose (dextrose)	B	C	A	B	A	B	A	A	A	-	A
glue (e.g. for wood)	B	-	B	-	A	-	A	-	A	-	-
glycerol	A	A	A	A	A	C	A	A	A	A	-
glycine, aqueous 10%	X	-	X	-	A	-	A	-	B	C	-
glycol - (see ethylene glycol)	-	-	-	-	-	-	-	-	-	-	-
glycolic acid, 30%	X	-	C	X	A	A	A	-	A	A	-
helium	A	A	A	A	A	A	A	A	A	A	-
heptane	A	A	A	A	X	-	A	-	B	C	-
hexanal	X	-	X	-	-	-	-	X	-	X	-
hexane	A	B	A	B	X	-	X	-	B	-	X
hexanetriol	X	-	X	-	A	-	A	-	A	-	-
hexanol	X	-	X	-	X	-	X	-	C	-	X
hexene	A	-	A	-	-	-	-	C	-	X	-
hydraulic fluid, hydraulic oils DIN 51 524	A	A	A	A	C	-	-	X	-	C	-
hydraulic fluid, oil-in-water-emulsion HFA	A	A	A	A	-	-	X	C	-	X	-
hydraulic fluid, phosphoric esters HFD	X	-	X	-	X	-	-	X	-	X	-
hydraulic fluid, polyglycol-water HFC	B	X	A	C	-	-	-	A	-	B	-
hydraulic fluid, water-oil-emulsion HFb	X	-	X	-	-	-	-	B	-	-	-
hydrazine	X	-	X	-	A	B	-	C	-	X	-
hydrazine hydrate	C	X	B	C	A	-	A	-	A	-	-
hydrobromic acid 50%	X	-	C	X	A	A	A	A	A	B	B
hydrochloric acid, 10%	X	-	B	C	A	B	A	B	A	B	C
hydrochloric acid, 3%	C	X	A	B	A	A	A	A	A	B	B
hydrochloric acid, 40%	X	-	X	-	B	C	B	C	X	-	A
hydrofluoric acid 10%	C	X	B	X	A	A	-	-	A	A	B
hydrofluoric acid 40%	X	-	C	X	A	B	-	-	A	A	B
hydrofluoric acid 70%	X	-	X	-	C	X	-	-	A	A	X
hydrogen	A	-	A	-	A	-	A	A	A	A	-
hydrogen cyanide	C	-	b	-	a	c	-	b	x	c	x
hydrogen peroxide, 3%	A	B	A	B	A	A	B	A	A	A	-
hydrogen peroxide, 30%	B	X	B	X	B	C	B	C	-	-	X
hydrogen sulfide, dry or wet	B	X	B	X	X	-	A	-	A	A	B
hydrogen sulfites	X	-	C	X	A	-	B	-	A	-	C
hydroquinone, aqueous	X	-	X	-	A	C	-	-	A	-	C
hydroxylchloric acid, aqueous	X	-	X	-	A	-	-	B	-	X	-
hydroxylamine sulfate	X	-	X	-	A	-	A	-	A	-	-
ink, for writing	A	-	A	-	A	A	A	-	A	-	-
iron sulfates, aqueous	B	C	A	B	A	-	A	-	A	-	-
iron(III)-chloride, aqueous 10%	B	C	A	B	A	-	A	B	A	A	-
isobutylalcohol	X	-	X	-	A	-	A	-	A	-	-
isoctane	A	B	A	C	X	-	X	-	A	-	-
isoctanol	X	-	X	-	X	-	-	B	-	C	-
isophorone	C	-	C	-	X	-	-	X	-	X	-

Media	Ester-PUR	Ether-PUR	Soft-PVC	TPV	Hypalon	Silicon	TPE				
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C
isopropanol (isopropyl alcohol)	B	X	A	X	C	X	-	-	X	-	X
isopropylacetate	C	X	B	X	C	X	-	-	X	-	X
isopropylbenzene (cumene)	X	-	C	X	X	-	X	-	X	-	X
isopropylchloride	X	-	X	-	-	-	X	-	X	-	X
isopropylether	C	X	B	X	C	-	X	-	B	C	X
ketones, generally (see exact media)	X	-	X	-	X	-	B	C	X	-	B
lactic acid, aqueous 3%	B	C	A	B	A	B	A	A	A	A	-
lactic acid, aqueous 50%	X	-	X	-	X	-	B	C	X	-	B
lactic acid, aqueous 10%	C	X	B	C	B	C	A	A	A	A	B
lanolin (wool fat)	A	A	A	A	B	X	X	-	C	-	C
laughing gas	A	-	A	-	A	-	A	-	A	-	A
lavender oil	B	-	-	-	-	-	X	-	X	-	X
lead acetates, aqueous	A	A	A	A	A	A	A	-	A	A	-
lead arsenate, aqueous	C	-	a	-	a	-	-	-	-	a	-
lead nitrate, aqueous	b	-	a	-	a	-	a	-	a	-	b
lead sulfate	A	-	A	-	A	-	-	-	A	-	B
lemon juice	B	-	A	-	A	-	-	-	A	-	B
lime - calcium oxide	-	-	-	-	-	-	-	-	-	-	-
limonene (dipentene)	B	-	B	-	-	-	X	-	X	-	B
linoleic acid	B	-	A	-	-	-	X	-	X	-	C
linseed oil (flaxseed oil)	B	C	B	C	B	X	B	-	A	-	A
liquide manure	X	-	A	-	A	-	-	-	A	-	A
lithium bromide	A	-	A	-	-	-	A	-	A	-	B
lithium chloride	A	-	A	-	A	-	-	-	A	-	A
magnesium chloride, aqueous 10%	A	X	A	C	A	B	A	A	A	A	-
magnesium hydroxide, aqueous	A	-	A	-	A	-	A	-	A	-	A
magnesium silikates (talc)	A	-	A	-	A	-	-	-	A	-	A
magnesium sulfate, aqueous	A	B	A	B	A	A	A	A	A	A	C
magnesium sulfites, aqueous	C	-	A	-	A	-	-	-	A	-	A
maize germ oil	B	C	B	C	B	C	-	-	A	-	B
maleic acid, aqueous	C	X	B	C	A	C	A	B	A	A	B
malic acid, aqueous (apple juice)	X	-	C	X	A	-	A	-	A	-	A
margarine	A	A	A	A	B	X	-	B	C	C	X
marsh	A	-	A	-	A	-	A	-	A	-	A
menthol	C	X	C	X	-	-	a	b	a	a	x
mercury	A	A	A	A	A	A	A	A	A	A	-
mercury nitrates	B	X	B	C	A	-	-	-	-	A	-
mercury salts, aqueous generally	X	-	X	-	B	-	A	-	A	-	A
mercury(II)-chloride	B	X	B	C	C	X	A	-	A	-	A
mesityl oxide	X	-	X	-	X	-	-	-	X	-	X
methane	A	-	A	-	A	-	X	-	B	-	C
methanol (methyl alcohol)	B	X	B	C	C	X	A	B	A	-	B
methyl acetate	X	-	X	-	C	X	A	B	X	-	X
methyl acrylate	X	-	X	-	X	-	-	-	X	-	X
methyl bromide	X	-	X	-	X	-	X	-	X	-	X
methyl chloride (see chloromethanes)	-	-	-	-	-	-	-	-	-	-	-
methyl chloroform trichloroethanes	-	-	-	-	-	-	-	-	-	-	-
methyl ethyl ketone (MEK)	X	-	X	-	X	-	C	X	C	X	X
methyl glycol - ethylene glycol	-	-	-	-	-	-	-	-	-	-	-
methyl isobutyl ketone	X	-	X	-	X	-	C	X	X	-	X
methyl pyrrolidone (NMP)	X	-	X	-	-	-	-	-	-	-	-
methylamine, aqueous	X	-	X	-	C	X	A	-	A	-	X
microbes (microorganisms)	X	X	A	A	A	B	C	A	A	C	C
mixed acid-sulfuric acid + nitric acid + water	A	-	A	-	A	-	A	-	A	-	A
mixed acid: sulfuric acid + phosphoric acid + water	X	-	X	-	B	-	B	X	A	-	X
molasses	X	C	B	X	A	B	A	B	A	A	A
morpholine	X	-	X	-	X	-	A	B	A	A	A
must (fruit wine)	A	-	A	-	A	-	A	B	A	B	X
mustard	A	-	A	-	A	-	-	A	-	-	-
myristyl alcohol (tetradecanol)	A	-	A	-	A	-	-	-	A	-	B
naphtha	B	-	B	-	X	-	C	X	X	-	X
naphthalene	C	X	C	X	X	-	X	-	C	X	X

Media	Ester-PUR	Ether-PUR	Soft-PVC	TPV	Hypalon	Silicon	TPE				
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C
natural gas, dry	A	-	A	-	A	X	C	X	C	X	-
natural gas, wet with 1-7 C-atoms	B	-	B	-	X	-	X	-	B	C	-
natural gas, wet with >7 C-atoms	A	-	A	-	C	X	-	C	B	C	-
nickel acetate	X	-	X	-	-	-	-	X	-	C	-
nickel chloride	B	X	A	C	A	-	A	-	X	-	C
nickel sulfate	B	C	A	B	A	A	A	A	A	B	-
nitric acid, 10%	X	-	X	-	B	C	A	B	A	B	C
nitric acid, 100%	X	-	X	-	X	-	C	X	X	-	-
nitric acid, 25%	X	-	X	-	C	X	B	C	B	C	-
nitric acid, 50%	X	-	X	-	X	-	C	X	B	X	-
nitrilotriethanol	X	-	X	-	X	-	-	-	B	-	A
nitrobenzene	X	-	X	-	X	-	X	-	X	-	-
nitrogen	A	-	A	-	A	-	A	-	A	-	-
nitrogen oxides (nitrous fumes)	X	-	X	-	X	-	X	-	C	-	-
nitroglycerin	X	-	X	-	A	C	-	-	A	-	X
nitromethane	X	-	X	-	B	-	C	X	X	-	-
nitropropanes	X	-	X	-	-	-	C	-	C	X	-
nitrotoluenes	X	-	X	-	X	-	X	-	X	-	-
nonyl alcohol nonanol)	X	-	X	-	-	-	-	B	-	B	-
octane	A	-	A	-	X	-	X	-	X	-	-
octanols (octyl alcohol)	X	-	X	-	X	-	A	-	A	-	B
oil, animal	A	A	A	A	B	C	C	X	B	C	-
oil, ASTM-oil nr. 1	A	A	A	A	C	X	X	-	B	C	C
oil, ASTM-oil nr. 2	A	A	A	A	C	X	X	-	B	C	B
oil, ASTM-oil nr. 3	A	C	C	X	C	X	C	X	B	C	B
oil, ATF-	A	A	A	A	-	-	C	X	C	X	-
oil, hydraulic - hydraulic fluid	A	A	A	A	B	X	C	C	B	C	-
oil, mineral	A	A	A	A	B	C	B	C	B	C	-
oil, vegetable	B	C	A	B	B	C	-	-	C	-	A
oleic acid	X	-	X	-	X	-	-	-	X	-	-
oleum	A	A	A	A	-	C	B	C	B	C	-
olive oil	C	X	B	C	C	C	X	X	A	B	C
ozone	C	-	C	-	C	-	C	-	A	-	B
palm oil	B	-	B	-	C	-	-	-	C	-	B
palmitic acid	A	-	A	-	C	-	C	X	C	X	-
para formaldehyde	B	-	A	-	-	-	-	-	-	A	-
paraffin (paraffin oil)	A	-	A	-	B	X	X	-	C	X	B
pectins	A	-	A	-	A	A	A	-	A	-	-
pentachlorphenol	X	-	X	-	-	-	-	-	C	-	-
pentanes	A	-	A	-	A	-	-	-	X	-	X
pentanol (amyl alcohols)	X	-	X	-	X	-	-	-	X	-	X
pentyl acetates	X	-	X	-	X	-	C	X	X	-	X
perchloric acid, aqueous	X	-	X	-	B	C	B	X	A	A	X
petroleum	C	-	X	-	X	-	X	-	C	X	-
petroleum ether	C	-	X	-	X	-	X	-	X	X	-
phenol	X	-	X	-	X	-	X	-	B	C	-
phenylhydrazine	X	-	X	-	X	-	C	X	C	X	-
phosgene	X	-	X	-	X	-	X	-	B	C	-
phosphoric acid 3%	B	C	A	B	A	A	A	A	B	C	-
phosphoric acid 50%	X	-	X	-	A	B	A	B	A	C	X
phosphorus trichloride oxide	X	-	X	-	X	-	b	c	a	a	C
photo developer, generally (see exact media)	X	-	X	-	b	-	a	-	a	-	b
photo emulsion, generally (see exact media)	X	-	X	-	B	-	A	-	A	-	B
photo fixing, generally (see exact media)	X	-	X	-	A	-	A	-	B	-	-
phthalic ester (phthalates)	X	-	C	-	X	B	B	C	A	B	X
picric acid	C	X	B	C	A	-	A	-	B	C	-
polychlorinated biphenyls	B	-	B	-	C	-	-	-	X	-	X
potash lye 10%	B	C	A	B	A	B	A	B	A	B	C
potash lye 50%	X	-	C	X	B	C	B	C	A	A	C
potassium acetate, aqueous	C	X	C	X	A	-	A	-	A	-	X
potassium borate, aqueous	C	x	b	x	a	-	a	-	a	-	-
potassium bromate 10%	X	-	X	-	A	-	A	A	A	B	C

Media	Ester-PUR	Ether-PUR	Soft-PVC	TPV	Hypalon	Silicon	TPE				
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C
potassium bromide, aqueous	C	X	B	X	A	-	A	A	A	A	-
potassium carbonate, aqueous (potash)	C	X	C	X	A	-	A	-	A	-	A
potassium chlorate, aqueous	C	X	A	C	A	A	A	A	A	B	C
potassium chloride, aqueous	B	X	A	C	A	A	A	A	A	B	C
potassium chromate, aqueous 40%	X	-	X	-	A	C	A	-	A	-	B
potassium cyanide, aqueous	C	X	C	X	B	-	A	-	A	-	B
potassium dichromate, aqueous 40%	X	-	C	X	B	C	A	-	A	-	C
potassium hydrogencarbonate	B	-	B	-	A	-	-	-	A	-	A
potassium hydrogensulfate, aqueous	X	-	C	X	-	-	A	-	A	-	B
potassium hydroxide (see potash lye)	-	-	-	-	-	-	A	-	-	-	-
potassium hypochlorite	X	-	X	-	A	-	-	-	C	-	C
potassium iodide, aqueous	X	-	X	-	A	-	A	A	A	A	B
potassium nitrate, aqueous	B	X	A	C	A	-	A	A	A	A	B
potassium perchlorate, aqueous	X	-	X	-	A	-	A	A	A	A	B
potassium permanganate, aqueous 5%	C	X	B	C	B	C	A	A	A	A	B
potassium peroxodisulfate	X	-	C	X	A	C	A	A	A	A	A
potassium phosphates	A	-	A	-	-	-	-	-	A	-	X
potassium sulfate, aqueous	A	C	A	B	A	A	A	A	A	B	-
potassium sulfite	A	-	A	-	A	-	-	-	A	-	A
propane, wet or gaseous	A	-	A	-	X	-	X	-	C	X	X
propargyl alcohol, aqueous 7%	X	-	X	-	-	-	B	C	B	C	B
propene (propylene)	X	-	X	-	-	-	X	-	X	-	X
propionic acid (propane acid)	X	-	X	-	A	-	C	X	C	X	-
propyl acetates	X	-	X	-	-	-	-	-	X	-	X
propylamines	X	-	X	-	-	-	-	-	X	-	X
propylene	X	-	X	-	B	-	-	-	X	-	-
propylene glycols (propanediols)	X	-	X	-	X	-	A	A	A	A	-
propylene oxide	X	-	X	-	-	-	A	-	X	-	X
pyridine	X	-	X	-	X	-	C	X	-	-	X
pyrrole	X	-	X	-	-	-	-	-	X	-	X
radiation, radioactive 108 Rad	B	B	B	B	C	C	-	-	A	-	X
radiation, ultraviolet	B	B	B	B	B	B	B	B	A	A	B
rapeseed oil	A	X	-	-	-	-	-	-	-	-	-
raw sugar juice	X	-	C	-	A	-	-	-	A	-	A
salicylic acid	B	-	A	-	A	C	A	-	A	-	A
sebacic esters	X	-	X	-	X	-	B	-	X	-	-
silver salts, generally (see exact media)	C	X	C	X	A	C	A	B	A	A	B
silicic acids, aqueous	X	-	C	X	A	B	A	A	A	B	C
silicium dioxide - silicic acids	-	-	-	-	-	-	-	-	-	-	-
silicon oil / -fat	A	B	A	B	X	-	-	-	B	C	B
silver nitrate, aqueous	X	-	X	-	A	C	A	B	A	A	B
sodium acetate, aqueous	C	X	B	X	A	-	A	-	A	-	B
sodium benzoate, aqueous	A	-	A	-	A	-	A	A	A	B	C
sodium bromide	-	-	-	-	A	-	-	-	A	-	-
sodium carbonate (soda ash)	C	X	B	C	A	B	A	A	A	A	A
sodium chlorate, aqueous	C	X	B	X	A	A	A	C	A	A	B
sodium chloride, aqueous (table-salt)	B	C	B	C	A	A	A	A	A	A	A
sodium chlorite, aqueous	-	-	-	-	B	X	A	C	A	A	-
sodium cyanide	C	X	C	X	A	A	A	-	A	-	A
sodium dichromate	C	X	C	X	X	-	-	-	A	-	B
sodium fluorides, generally	C	X	C	X	A	-	-	-	A	-	B
sodium hydrogencarbonate, aqueous	C	X	C	X	A	-	A	A	A	A	-
sodium hydrogensulfate	C	X	B	X	A	-	A	-	A	-	A
sodium hydrogensulfite, aqueous 10%	B	X	B	X	A	A	A	B	A	A	-
sodium hydroxide (caustic soda), aqueous 10%	C	X	B	C	A	B	A	B	A	A	B
sodium hydroxide (caustic soda), aqueous 50%	X	-	X	-	X	-	C	X	A	A	C
sodium hypochlorite, aqueous 10%	C	X	B	C	A	-	C	X	A	B	C
sodium metaphosphates	A	-	A	-	A	-	-	-	B	-	A
sodium nitrate, aqueous 10%	B	C	B	C	A	B	A	A	A	B	-
sodium nitrite	C	X	B	X	A	A	A	A	A	B	C
sodium perborate	X	-	X	-	B	C	A	-	A	-	A
sodium phosphates	B	C	B	C	A	A	A	A	A	B	-



Media	Ester-PUR	Ether-PUR	Soft-PVC	TPV	Hypalon	Silicon	TPE				
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C
sodium silicate, aqueous	X	-	C	-	A	-	-	A	-	A	-
sodium sulfate, aqueous (Glauber's salt)	B	C	A	B	A	A	A	A	A	A	-
sodium sulfides	B	-	B	-	A	-	A	B	A	B	-
sodium sulfite, aqueous 3%	A	B	A	B	A	A	A	B	A	A	-
sodium thiosulfate	B	-	A	-	A	A	A	A	A	A	-
solvents, generally (see exact media)	X	-	X	-	X	-	X	-	X	-	-
soybeans oil	A	-	A	-	B	X	B	C	B	-	A
spirits	A	-	A	-	A	A	-	A	A	A	-
starch sugar	B	C	B	C	A	-	A	-	A	A	-
starch, aqueous	X	-	X	-	A	-	A	A	A	A	-
steam of oleum	X	-	X	-	C	-	-	C	-	X	-
stearic acid	C	X	B	C	A	B	B	C	A	C	A
styrene	X	-	X	-	X	-	X	-	X	-	-
succinic acid, aqueous	X	-	C	X	A	A	A	A	A	B	X
sugar syrup (saccharose)	B	C	A	B	A	B	A	A	A	A	A
sugar, dry	A	B	A	A	A	A	A	A	A	A	-
sulfonic acids, generally	X	-	X	-	A	B	B	C	A	-	A
sulfur trioxide (sulfur acid anhydride)	X	-	X	-	X	-	X	-	X	-	-
sulfuric acid, 25%	X	-	C	X	B	C	A	B	A	B	C
sulfuric acid, 3%	C	X	A	B	A	A	A	A	A	A	C
sulfuric acid, 50%	X	-	X	-	C	X	B	C	B	C	X
sulfuric acid, 90% (fuming, oleum)	X	-	X	-	X	-	X	-	C	X	X
sulphur hexafluoride	-	-	-	-	-	-	-	-	-	-	-
tallow (talcum)	B	C	B	C	A	-	B	C	A	A	A
tanning acid - tannine	-	-	-	-	-	-	-	-	-	-	-
tannins (tanning acid)	C	B	B	C	A	-	A	-	A	A	-
tar (tar oil)	X	-	X	-	C	X	-	-	X	-	C
tartaric acid, aqueous	B	C	A	B	A	-	A	A	A	A	-
tea tree oil	B	-	B	-	-	-	-	B	-	C	-
tee, aqueous	-	-	-	-	A	A	-	-	-	-	-
tetrachlorocarbonates - chloromethanes	-	-	-	-	-	-	-	-	-	-	-
tetrachloroethane	X	-	X	-	X	-	X	-	X	-	-
tetrachloroethylene (perchloroethylene)	X	-	X	-	X	-	X	-	C	X	X
tetrahydrofuran	X	-	X	-	X	-	X	-	X	-	X
Tetralin (tetrahydronaphthalene)	X	-	X	-	X	-	X	-	X	-	-
thionyl chloride	X	-	X	-	X	-	X	-	A	-	X
thiophene	X	-	X	-	X	-	X	-	X	-	X
tin-II-chlorides, aqueous	C	X	B	C	A	B	A	B	B	C	B
tincture of iodine	X	-	X	-	B	-	-	B	-	X	-
toluene	X	-	X	-	X	-	X	-	X	-	X
town gas, free of benzene	A	-	A	-	A	-	C	X	C	X	-
transformer oil (see oil)	-	-	-	-	-	-	-	-	-	-	-
tributyl phosphate	X	-	X	-	X	-	-	X	-	X	-
trichlorethanes (methyl chloroform)	X	-	X	-	C	-	-	X	-	X	-
trichloroacetic acid	X	-	X	-	B	-	C	-	C	X	X
trichloroethylene	X	-	X	-	X	-	X	-	X	-	-
trichloromethanes (see chloromethanes)	-	-	-	-	-	-	-	-	-	-	-
tricresyl phosphate	X	-	X	-	X	-	B	-	X	-	X
triethylene enamine	B	-	B	-	B	-	-	-	X	-	A
triethylene glycol	B	C	B	C	-	-	A	-	A	-	B
turpentine	X	-	X	-	X	-	X	-	X	-	-
turpentine, oil of	X	-	X	-	X	-	X	-	X	-	-
urea, aqueous	C	X	C	X	A	C	A	-	A	-	C
urine	A	-	A	-	A	-	-	A	-	A	-
varnish	C	-	B	-	X	-	-	X	-	X	-
vaseline	A	-	A	-	B	X	-	-	X	-	B
vinegar	X	-	C	-	B	-	-	C	-	A	-
vinyl acetate	X	-	X	-	X	-	-	-	C	-	X
vinyl chloride	X	-	X	-	X	-	b	c	X	-	X
waste water	X	-	-	-	a	-	-	-	A	-	B
water	A	C	A	A	A	A	A	A	A	A	A
water, mineral water - water	B	C	A	-	A	A	A	A	A	A	-

Media	Ester-PUR	Ether-PUR	Soft-PVC	TPV	Hypalon	Silicon	TPE				
	23 °C	60 °C	23 °C	60 °C	23 °C	60 °C	23 °C	80 °C	23 °C	80 °C	23 °C
water, sea water/ salt water - eau	A	C	A	A	A	A	A	A	A	A	A
water-glass, aqueous	X	-	C	X	A	B	A	A	A	B	C
weathering, generally	B	B	B	B	B	C	B	B	B	B	B
whale oils	B	-	B	-	B	-	-	-	C	-	A
wine	A	-	A	-	A	-	A	-	A	-	A
wood oil	C	-	B	-	C	-	-	-	C	-	C
XYLAMON	C	-	C	-	-	-	X	-	X	-	X
xlenes	X	X	X	X	X	-	X	-	X	-	X
yeast, aqueous	X	-	A	-	A	-	A	-	A	-	A
zinc acetate, aqueous	X	-	X	-	X	-	-	-	B	-	X
zinc chloride, aqueous	B	C	B	C	A	B	A	A	A	A	-
zinc sulfate, aqueous	B	C	B	C	A	A	A	A	A	A	-

LEGENDA

A	优异 / Excellent
B	优良 / Good
C	适用 / Suitable
X	请勿使用 / Do not use